



CPS 1050 UV Coating

Technical Data Sheet

CPS 1050:

CPS 1050 is a fully formulated UV coating that exhibits excellent wetting properties and durability.

Handling and Storage:

CPS 1050 is stable for up to 6 months at ambient conditions.

Refrigeration will improve shelf life. Elevated temperatures will decrease shelf life.

This product is light sensitive and should not be exposed to daylight, UV light and artificial lighting during storage. Exposure to daylight, UV light and artificial lighting should be kept to a minimum during handling.

General information:

CPS 1050 is a fully formulated UV coating that exhibits good durability and excellent wetting properties. Spray coat without dilution. Low oxygen inhibition.

Physical Properties:

Tensile Modulus	ASTM D638-10	330 MPa
Strength		12 MPa
Elongation		7%
Shore D Hardness	ASTM D2240-15	57 D
Viscosity		70 cPs @ 25 °C