



## CPS 1050 W Wood Coating

### *Technical Data Sheet*

---

#### **CPS 1050 W:**

CPS 1050 W is a fully formulated UV coating designed specifically for wood coating applications.

#### **Handling and Storage:**

CPS 1050 W is stable for up to 6 months at ambient conditions.

Refrigeration will improve shelf life. Elevated temperatures will decrease shelf life.

This product is light sensitive and should not be exposed to daylight, UV light and artificial lighting during storage. Exposure to daylight, UV light and artificial lighting should be kept to a minimum during handling.

#### **General information:**

CPS 1050 W is a fully formulated UV wood coating with great wetting properties and durability. Spray coat without dilution. Low oxygen inhibition.

#### **Physical Properties:**

Adhesion to Wood	ASTM D3359-09	5
Tensile Modulus		330 MPa
Strength	ASTM D638-10	12 MPa
Elongation		7 %
Shore D Hardness	ASTM D2240-15	57 D
Viscosity		70 cPs @ 25 °C