



CPS 1060 Wood Coating

Technical Data Sheet

CPS 1060:

CPS 1060 is a fully formulated UV coating designed specifically for wood coating applications.

Handling and Storage:

CPS 1060 is stable for up to 6 months at ambient conditions.

Refrigeration will improve shelf life. Elevated temperatures will decrease shelf life.

This product is light sensitive and should not be exposed to daylight, UV light and artificial lighting during storage. Exposure to daylight, UV light and artificial lighting should be kept to a minimum during handling.

General information:

CPS 1060 is a fully formulated UV wood coating that exhibits great hardness and flexibility, low oxygen inhibition. This formulation can be spray coated without dilution.

Physical Properties:

Adhesion to Wood	ASTM D3359-09	5
Tensile Modulus		600 MPa
Strength	ASTM D638-10	23 MPa
Elongation		9 %
Shore D Hardness	ASTM D2240-15	60 D
Viscosity		90 cPs @ 25 °C