

CPS HT511-LCD High Temperature Material

General Information

CPS HT511-LCD is a fully formulated resin that is tuned to print on LCD 3D printers to create a polymer with high strength and HDT.

Product Data

Viscosity (cps @25 °C)	640	Method	Brookfield SP #31
Bulk Properties			
Tensile Modulus (mPa)	1040	ASTM D 638-14	
Tensile Strength (mPa)	45	ASTM D 638-14	
Elongation (%)	5.6	ASTM D 638-14	
Shore Hardness	86 D		
Heat Deflection Temperature (°C)	0.45 mPa: 97 1.8 mPa: 70	ISO 75-1, 75-2	

Print Settings

CPS HT511-LCD is recommended 60s for first layers, and 5-9 seconds for the model layers, depending on the printer.

Post Cure Procedure

Post curing is not necessary, but may improve surface quality. For best results post cure uniformly under broadband light at 30 mW/cm² for 10 minutes, then anneal 5°C above working temperature for 1 hr

Storage and Handling

CPS HT511-LCD stable for up to 1 year at ambient conditions.

This product is light sensitive and should not be exposed to daylight, UV light and artificial lighting during storage.

Exposure to daylight, UV light and artificial lighting should be kept to a minimum during handling.

Arkema Inc., 3D Printing Development Center

1880 S. Flatiron Ct STE J, Boulder, CO 80301

Please consult Arkema's disclaimer regarding the use of Arkema's products on <https://www.arkema.com/global/en/products/product-safety/disclaimer/>

Arkema - a French société anonyme, registered in the Nanterre (France)
Trade and Companies Register under the number 319 632 790

[arkema.com](https://www.arkema.com)

ARKEMA