

PR221-LCD Gray Prototyping Resin

General Information

PR221-LCD is formulated to work with LCD 3D printers using 385-405 nm light. It is tuned to print with high resolution and reliability. This resin is offered in a gray color that shows detail well.

Chemical Data

		Method
Viscosity (cps @24.3 °C)	700	Brookfield SP #31
	Post-cured	
Tensile Modulus (mPa)	1270	ASTM D 638-1V
Tensile Strength (mPa)	58	ASTM D 638-1V
Elongation (%)	5	ASTM D 638-1V
Shore Hardness	86.5 D	

**Parts were post-cured for 10min a side with a Broadband light source at 10mW/cm² for 10 minutes a side.*

**Properties may vary in orientation and post-treatment.*

Print Settings

PR221-LCD is recommended 60s for first layers, and 5-9 seconds for the model layers, depending on the printer.

Post Cure Procedure

Parts should be post cured under a either a 395-405 nm LED for 10 minutes on a side at a minimum of 10 mW/cm² or a broadband UV light source at 10 minutes a side to bring the parts up to their full properties

Storage and Handling

PR221-LCD stable for up to 1 year at ambient conditions.

This product is light sensitive and should not be exposed to daylight, UV light and artificial lighting during storage.

Exposure to daylight, UV light and artificial lighting should be kept to a minimum during handling.

Arkema Inc., 3D Printing Development Center

1880 S. Flatiron Ct STE J, Boulder, CO 80301

Please consult Arkema's disclaimer regarding the use of Arkema's products on <https://www.arkema.com/global/en/products/product-safety/disclaimer/>

Arkema - a French société anonyme, registered in the Nanterre (France) Trade and Companies Register under the number 319 632 790

arkema.com